

HPVA Laboratories 42777 Trade West Drive, Sterling, VA 20166 PHONE 703-435-2900 FAX 703-435-2537

Report On Critical Radiant Flux of Floor-Covering Systems Using a Radiant Heat Energy Source As Determined By ASTM E 648 Test Method

PREPARED FOR: **Armstrong Flooring Inc.**Lancaster, PA

TEST NUMBER: FRP-1064 R1

2.0mm Heterogeneous Vinyl Sheet

Date of Issue: 1/29/2018

Revision Date: 5/7/2024





HPVA Laboratories 42777 Trade West Drive, Sterling, VA 20166 PHONE 703-435-2900 FAX 703-435-2537

I. SCOPE

This report contains the reference to the test method, purpose, test procedure, preparation and conditioning of test samples, description of materials, test and post test observation data, and test results.

II. TEST METHOD

The test was conducted in accordance with ASTM Designation E648-17, "Standard Method of Test for Critical Radiant Flux of Floor Covering Systems Using a Radiant Heat Energy Source." The test is also known as NFPA No. 253.

III. PURPOSE

The purpose of the test is to determine the critical radiant flux of horizontally-mounted floor covering systems exposed to a flaming ignition source in a graded radiant heat energy environment maintained in a test chamber. The specimen may be mounted over underlayment, a simulated concrete structural floor, bonded to a simulated structural floor, or otherwise mounted in a typical and representative way.

The test method provides a basis for estimating one aspect of fire exposure behavior for floor covering systems. The imposed radiant flux is designed to simulate the thermal radiation levels likely to impinge on the floors of a building whose upper surfaces are heated by flames and/or hot gases from fully developed fire in an adjacent room or compartment. The method was developed to simulate an important fire exposure component of fires which may develop in corridors or exit ways of buildings and is not intended for routine use in estimating flame spread behavior of floor covering in building areas other than corridors or exit ways.

IV. TEST PROCEDURE

The basic elements of the test chamber are: 1) an air-gas, fueled radiant heat energy panel inclined at 30° to and directed at 2) a horizontally-mounted floor covering system specimen. The radiant panel generates a radiant energy flux distribution ranging along the 100-cm length of the test specimen from a nominal maximum of 1.0 watts/cm2 to a minimum of 0.1 watts/cm2. The test is initiated by open flame ignition from a pilot burner. The distance burned to flame-out is converted to watts/cm2 and reported as **critical radiant flux**.



Test Number: FRP-1064 R1

HPVA Laboratories 42777 Trade West Drive, Sterling, VA 20166 PHONE 703-435-2900 FAX 703-435-2537

Report on Critical Radiant Flux of Floor Covering Systems Using a Radiant Heat Energy Source as Determined by the ASTM E 648 Flooring Radiant Panel

01/23/18

Test Date:

Report Prepared For:	Armstrong Flooring Inc.
	Lancaster, PA
Material Tested:	2.0mm Heterogeneous Vinyl Sheet

Sample Information:				
Detailed Product Description: Sample Preparation:	2.0mm Heterogeneous Vinyl Sheet. Vinyl sheet with a 0.55mm wear layer, Width: 2000mm, Gauge: 2.0mm. Production Date: 12/04/17, Lot Number: 1712045151. The material was adhered to a 1/4" cement board backer by the manufacturer using Armstrong S240 adhesive.			
Sample Selection By:	Manufacturer		Flux Profile Run Date:	01/23/18
Number of Samples:	3	•	Conditioning Days:	11
Surface Exposed:	Surfaces (Face Side Only)	•	Sample Color:	Brown
Average Thickness (in.):	0.341		Average Weight (lbs):	6.60

Test Data			
	Burn 1	Burn 2	Burn 3
Preheat Time (min):	5:00	5:00	5:00
Starting Temp. (°C):	177	177	178
Burn Length (cm):	21.5	19.8	17.3
Time to Max Burn Length (min):	10.10	10.05	10.02

Test Results			
	Burn 1	Burn 2	Burn 3
Critical Radiant Flux (W/cm2):	0.83	0.87	0.90
	Average Critical Radiant Flux (W/cm2):		0.87
	Standard Deviation:		0.03
	Coefficient of Variation:		3.62

Observations:	All Burns: Blistering during the 5 minute preheat.		
Remarks:	Reported weights and thicknesses include the 1/4" cement board backer. Revision 1 issued 05/07/2024 - Product Description/Material Tested changed to "2.0mm Heterogeneous Vinyl Sheet" at the request of the client. "Comparable Products" removed from Detailed Product Description section on page 3.		
Conclusions:	The product is classified as Class I (Critical Radiant Flux greater than 0.45 W/cm^2) by NFPA 101.		
Test Operator:	СР		

Report Prepared and Reviewed By:

Sr. Manager of Product Testing